


Project:

Order No: Premio Carbon EPS100 Compression
Part No: P100Carbon/2019_02_15(1)
Customer: Premio Hungária

Tester: Thümler GmbH-Z5
Method: MSZ EN 826
Execution date: 2019. 02. 15. 9:11:56

Chart:



Results:

Nom	Stress [kPa] ,max.	Displacement [mm] ,max.
P100Carbon/2019_02_15(1)	115,80	9,99
P100Carbon/2019_02_15(2)	113,07	9,99
P100Carbon/2019_02_15(3)	114,91	10,00
P100Carbon/2019_02_15(6)	115,06	9,99
Max.	115,80	10,00
Min.	113,07	9,99
Mean	114,71	9,99